

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 10-053679

(43)Date of publication of application : 24. 02. 1998

(51)Int. Cl. C08L 25/02
C08K 3/00
C08K 3/24
C08K 3/26
C08K 5/09
C08K 5/20

(21)Application number : 08-210831 (71)Applicant : DAICEL CHEM IND LTD

(22)Date of filing : 09. 08. 1998 (72)Inventor : YUGAWA TAKAO
TADA HEIHACHIRO
ITAKURA MASAHIKO

(54) STYRENE POLYMER COMPOSITION

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a styrene polymer composition capable of exhibiting excellent strength, moldability and heat-resistance in balanced state without deteriorating the transparency and useful in the field of food container, light electric appliance, etc., by compounding a styrene polymer with a specific lubricant and an inorganic filler having a specific particle diameter.

SOLUTION: This composition is produced by compounding (A) 100 pts.wt. of a styrene polymer with (B) 0.001-3 pts.wt. of an inorganic filler having an average particle diameter of 0.001-10 μ (e.g. barium sulfate or calcium carbonate) and (C) 0.001-3 pts.wt. of a lubricant consisting of a higher fatty acid (e.g. stearic acid or behenic acid), a higher fatty acid salt (e.g. zinc stearate or sodium stearate) or a higher fatty acid amide (e.g. stearylamine or ethylenebisstearylamine).

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision
of rejection][Kind of final disposal of application
other than the examiner's decision of
rejection or application converted
registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against
examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998, 2000 Japanese Patent Office